

## **BEGER ONE**

## Acrylic Emulsion Paint & Primer in 1: for Interior

	Acrylic Emulsion Paint & Primer in 1 : for Inte	rior
Description	Beger One is matt interior paint and primer in one, which is exceptional hide with Max-Cover Tital technology combined with acrylic resin from Germany's technology, consequently. It is high concentrate that giving a perfect finish in just one coat while conventional paint need 3 times. It has helped to save time, labor cost and paints. Furthermore it has silver iron inside to ant-microbial growth activity and very odor therefore can move inside just 5 minutes after paint dry.	e paint e your
Feature and Benefits	* Matt interior.  * Give a percect finish in hust one coat.  * Excellent hiding.  * Low VOCs, low odor, environmental friendly.  * Anti-microbial.  * Highly scrub resistance.	
Properties for Use	Beger One use as a interior top coat on cured cement, gypsum.	
Film Thickness and Spreading Rate	Minimum Maximum Typical	
* Dry film thickness (microns)  * Wet film thickness (microns)  * Theoretical coverage rate (m²/Litre/coat)	80       100       0         170       210       0         7       8.5       Actual consumption rate depends onapplic method and surface condition.	cation
Physical Properties		
<ul> <li>* Vehicle type</li> <li>* Finish</li> <li>* Colour</li> <li>* Specific gravity</li> <li>* Solid by volume</li> <li>* Dry time (@25'C, 30 mm.DFT)</li> <li>Touch dry</li> <li>Dry to handle</li> </ul>	: Acrylic Emulsion : Matt : According to the "Beger One" : 1.44-1.49 : 56.5-59.0 : 20 minutes : 45-60 minutes	
Application Method		
* Tool * Thinner * Condition during application	<ul><li>: High quality roller.</li><li>: Not recommended diluted.</li><li>: The moisture content in the concrete should not exceed 14%.</li><li>: Concrete and masonry cure at least 30 days before coating.</li></ul>	
Application System		
* Typical paint system	If the surface's moisture content more than 14%, apply Beger Multi-Purpose Primer #B-1900  : Lightweight concrete and pre-cast walls  * Primer : Beger Skim Cote #101 and : Beger Cool All Plus Alkali Resisting Primer #5000 or : Beger Skim Cote #102 without primer #5000 or : Beger Skim Cote #102 without primer # 1  * Top coat : Beger One : Old masonry or deteriorated surfaces  * Primer and top coat : Beger One : In case chalky conditions, apply Beger Multi-Purpose Primer #B-1900 : Painted surfaces, in case light shade of Beger One over painted deep shade wall, 2nd coat of Beger One must be applied to cover that area.	mount Beger gicidal  coat coat coat coat coat coat coat coa
Storage	: The product must be stored in accordance with national regulations. Storage conditions are to keep the	ì
	containers in a dry, cool, well ventilated space and away form source of heat an ignition.  : Containers must be kept tightly closed.  : 6-12 months at ambient.	
Health and safety	: Use under well ventilated conditions. : Do not breathe or inhale mist. : Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and : Eyes should be well flushed with water and medical attention sought immediately.	water.
Precaution	: Keep out of reach of children.	
Reference Standard	: TIS 2321-2549 Weather Resistant Emulsion Paint for Interior.	
Packing Size	: 3 litres and 8 litres.	



DISCLAIMER TECHNICAL DATA SHEET

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience.

However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itselt. We reserve the right to change the given data without notice.

Page : 1 of 1 Beger One

Edition: October 2016